TECHNICAL INFORMATION

Edition 2026

Docril® N
waterproof

DOCRIL N

PFAS FREE

HEAVY METALS FREE

MARINE

Roll lenght:	60 m	(65,6 yards)	

PROPERTIES



Composition:	100% Solution Dyed Acrylic		
Width:	120 cm (47") – 153 cm (60")		
Weight:	335 g/m²	(9.8825 oz/yd²)	UNE 40339
Water penetration resistance:	≥ 105 cm H_2O	(≥ 40" H_2O)	UNE EN ISO 811
Resistance to surface wetting – Spray Test:	100 note (max. 100)		UNE-EN ISO 4920
Warp/Weft tensile strength:	140/90 daN/5 cm	(314/202 lbf/2 in.)	UNE-EN ISO 13934-1
Warp/Weft elongation at break:	≤ 25/≤ 25 %		UNE-EN ISO 13934-1
Warp/Weft tear strength:	4/3 daN	(11,3/6,8 lbf/2 in.)	UNE-EN ISO 13937-2
Colour fastness to artifical light:	≥ 7 note blue scale (max. 8)		UNE-EN ISO 105-B02
Colour fastness to artifical weathering:	≥ 7 note blue scale (max. 8)		UNE-EN ISO 105-B04
Colour fastness to seawater:	5 note (max. 5)		UNE-EN ISO 105-E02
Colour fastness to chlorinated water (from pools):	5 note (max. 5)		UNE-EN ISO 105-E03

Tolerance +/- 5% average values. Non-contractual information. The data are result of tests performed in our laboratories.
For more technical information, please contact us at info@citel.com

CARE&CLEAN



Maintenence instructions: Remove dust with a vacuum cleaner, without rubbing. Clean with a sponge or a soft brush dampened with water and soap.
When used in awnings, it is very important to allow the fabric to dry completely before roll it up

WARRANTY



APPLICATIONS

